

COLORTEC PETRA

Grout for Natural & Artificial Stone

Description:

COLORTEC PETRA is a high performance mortar for grouting up to 25 mm joints between stone blocks. It is an improved cementitious grout consisting of hydraulic binder, silica, polymer resin and special additives. COLORTEC PETRA is specially recommended for indoor and outdoor grouting of floors and walls in marble, granite and all types of natural and artificial stone. It is designed to fill grout joints up to 25 mm wide forming a smooth, compact surface that is easy to clean without surface efflorescence.

Uses:

COLORTEC PETRA is used to fill joints in installation of natural and artificial stone, marble, and granite for:

- Facades and walls.
- Balconies and terraces.
- Bathroom and showers.
- Heated and unheated floors.
- Tiles set without joints.
- Pre-polished tiles.
- Floors subject to heavy foot traffic such as shopping centers, railway stations, undergrounds and airports.

Advantages:

- Once cured it forms a compact resistant surface.
- Non shrinkage.
- High abrasion resistance.
- Easy to apply and easy to clean.
- Hardens without cracks and forming a smooth surface.
- Waterproof.
- Weather condition resistant.

Instructions for Use:

The stone adhesive must be sufficient dry before filling the joints. The joints must be dry, clean and empty down to 2/3 of their depth.

Mixing:

Pour the water in a clean container, then add COLORTEC PETRA bag and mix until a homogeneous, runny and lump-free mix is obtained. Depending on the application, mix a bag of 25 Kg. of COLORTEC PETRA with:

- 8.75 to 9.5 Lt. of water (for floors)
- 7.50 to 8.75 Lt. of water (for walls)

Let the mix set for about three minutes and then mix again briefly just before using. Never add additional water to a mix that has begun to set.

Application:

Fill the joints fully with the COLORTEC PETRA mix using a rubber trowel or float. Remove excess mix from the surface and move the trowel diagonally across the joints while the mix is still wet.

In warm, dry weather, wetting the joints before applying the mix can help to prevent the grout from drying too quickly.

Let COLORTEC PETRA set in the joints for 15 – 20 minutes and clean off the residue with a wet sponge moving diagonally across the joints and without pressure. Rinse the sponge and change the water frequently.

Perform the final cleaning of the surface of the tiles with a wet cloth or a sponge once setting is completed (at least 3 hours after application). Washing the floor tiles too early can wash some of the grout out of the joints. Yet when left until the grout has hardened completely, the floor has to be cleaned by mechanical means, which may scratch the surface.

COLORTEC PETRA

Standards:

- European norm EN 13888 as CG2 AW
- ANSI A 118.7 – 1999
- ASTM C 109

Packaging:

COLORTEC PETRA Available in polythene-lined bags of 25 Kg.

TECHNICAL PROPERTIES	
Appearance	: Powder
Color	: Refer to grout color Chart
Wet Density	: 1.85 Kg. /Lt. @ 20°C
Dry Density	: 1.6 Kg. /Lt. @ 20°C
Application Temperature	: +5°C to +35°C
Workable time of the mix	: 30 – 40 minutes
Resistance to solvents and oil	: Excellent
Resistance to alkalis	: Excellent
Compressive Strength	: 30 N/mm ²
Flexural Strength	: 8.0 N/mm ²
Tensile Strength	: 4.0 N/mm ²
Shrinkage (fully cured)	: <1.5 mm/m
Water Absorption	: <5 g

Consumption:

Consumption varies with the size of the tiles width and depth of the joints. Use the following formula to calculate the consumption:

Formula:
$$\frac{A + B}{A \times B} \times W \times D \times 1.6 = \text{Kg./m}^2$$

W = width of joint (mm)
D = thickness of tile (mm)
A = length of tile (mm)
B = width of tile (mm)

Cleaning:

All used tools should be cleaned with water before the product cures.

Storage:

Store in dry covered place in original well closed packaging. Shelf life is 12 months if stored as recommended

Recommendations:

- Do not apply COLORTEC PETRA when temperature is less than +5°C or more than +40°C.
- Apply COLORTEC PETRA when the joint is totally dry.
- Perform a test of grouting and cleaning before using a porous natural or artificial stone installment.
- Natural or artificial stone that is sensitive to acids such as marble, travertine, etc., must not be cleaned with acid-based cleaners.
- COLORTEC PETRA cannot be mixed with other hydraulic binders.
- Expansion and fraction joints cannot be filled with COLORTEC PETRA.
- When resistance to acids or hygiene application is required, use COLORTEC POXY.

Health and Safety:

COLORTEC PETRA is a cement based product. Avoid contact with skin or eyes. Provide adequate ventilation and avoid inhalation of dust.

MATEX Rev.03-0720

This technical data sheet is not considered as local building codes. It shall be used as general reference for the product, based on our current knowledge and experience. However the company do not accept any liability arising from the use of its products as it has no direct control on how and where the product is applied.

