

# HYDROBIT RBH

## Rubberized Cold Applied Bituminous Coating

### Description:

HYDROBIT RBH is a High Build cold applied water based non-fibrated bitumen emulsion. It is a mix of selected bitumen emulsified with water and the addition of special additives, to give an easy applied protective coating. HYDROBIT RBH, once dries gives a firm, flexible, jointless waterproofing and protective coating to the substrate.

HYDROBIT RBH is suitable waterproofing of concrete, asphalt, metal, roofing felt and other similar surfaces.

### Applications:

- Can be used for general waterproofing applications.
- Waterproofing for wet areas such as kitchens and bathrooms.
- Damp proofing of cement sheets, facades, etc.
- Cement pipes and metal. Protection against corrosion.
- Waterproofing coat for concrete footings and retaining walls.
- For maintenance of roofs including light weight screed, bitumen sheets, asbestos, slate, built up felt, etc.
- Acts as a vapor/salt barrier for exterior walls behind granite, marble, cladding, curtain walls, etc.
- To provide waterproofing separation layer between screed flooring.
- As a curing compound on freshly casted concrete substructure.

### Advantages:

- Vapour permeable allows substrate to breathe.
- Reduced chloride penetration.
- Simple and easy to use.
- Solvent free and cold applied.

- Seamless, asbestos free, flexible. Coating once cured.
- Easy application due to paintable consistency.
- Can be applied on damp surfaces.
- Compatible to all bituminous products.
- Excellent resistance to mild acids and alkalis.
- Can be used as waterproofing, protection and curing when applied on concrete substructure

### Instructions for Use:

#### Surface Preparation:

All surfaces should be sound, clean, dry and free from loose material, efflorescence, laitance, curing compounds, dirt, oil and grease.

Cut and reseal blisters in asphalt or roofing. Remove chippings other than those that form the surface of mineralized felt. Porous surfaces such as concrete and fiber reinforced cement should be primed using HYDROBIT diluted 1:2 with clean water. Old concrete and steel must be structurally sound prior to application.

#### Mixing:

HYDROBIT RBH is a single component ready to use emulsion. Shake the barrel well to mix any settled material prior to application.

#### Application:

HYDROBIT RBH can be applied with a roller, trowel, brush or a spraying machine. It is recommended to apply two coats in case of roller or brush applications. Second coat should be applied at right angle to the first coat.

HYDROBIT RBH may be applied to damp but not wet surfaces. Dampen brushes before and occasionally during use to avoid clogging and to ensure ease application. During hot, dry weather application may be assisted by dampening the surfaces which to be treated.

# HYDROBIT RBH

When subsequent coats are applied recoat interval is 60 min before the next coat in order to avoid possible air bubbles due to evaporation of water in the subsequent coat.

To provide a good key to tiles fixing on top of screed, plastering, or for protection against foot traffic, spread the second coat while it is still tacky with clean sand.

HYDROBIT RBH can be applied on several kind of surfaces such as concrete, blocks, brick, corrugated sheets, asbestos. For application on metal surface (zinc, steel, etc.), it is not recommended to keep it exposed as the coating will be soften and crack due to high temperature climate.

For waterproofing the underground structures, such as footings, HYDROBIT RBH can be applied into green concrete immediately after removing the shutter. The applied coat will act as an effective curing membrane to the concrete. Apply the second coating once the first coat is dry. Backfill once the final coat is totally dry. Ensure that the applied coating is not getting damaged while backfilling due to ongoing site activities.

HYDROBIT RBH can be applied as an adhesive to fix insulation boards such as cork and polystyrene to the concrete.

## Technical Compliance:

HYDROBIT RBH conforms to:

- ASTM D1187, D2939, C309
- BS 8102

## Packaging:

HYDROBIT RBH is available in 20 liter pails and 200 liter barrels.

## Coverage:

HYDROBIT RBH achieves coverage of 2 to 4 square meters per liter per coat.

## TECHNICAL PROPERTIES

Appearance	:	Dark black/brown coating. Cures to a hard tack free finish.
Solid Contents	:	60 to 65%
Rubber Content	:	10%
Specific Gravity	:	1.05 @ 25°C
Service Temp.	:	-10°C to + 85°C
Flashpoint	:	Non flammable
Drying Time	:	4 hours at 35°C
Over Coating Time	:	14 hours at 35°C
Elongation	:	>100%
Application Temperature	:	+5 to +55°C
Water Resistance	:	Excellent
Chemical Resist.	:	Aqueous groundwater salt solutions, mild detergent, acids and alkalis

## Storage:

Stored in original packing in dry conditions away from direct sunlight and high humidity levels.

## Shelf Life:

HYDROBIT RBH can be utilized within 12 months of production date if stored in proper conditions in unopened original packing.

## Cleaning:

Clean all tools with clean water before product hardens.

## Health and Safety:

- Use goggles and gloves during application. Do not breathe the vapor of the product. Use only in well ventilated areas.
- Avoid contact with eyes or skin.
- In case of eyes contact, clean immediately with plenty of clean water and seek medical care.

MATEX Rev.03-0221

This technical data sheet is not considered as local building codes. It shall be used as general reference for the product, based on our current knowledge and experience. However the company do not accept any liability arising from the use of its products as it has no direct control on how and where the product is applied.

