

HYDROCRYL 300

Flexible Acrylic Based Waterproofing Membrane

Description:

HYDROCRYL 300 is an elastomeric single component liquid applied acrylic waterproofing membrane. It cures to a tough, elastic and durable waterproofing film; having resistance to weathering and UV exposure. HYDROCRYL 300 has excellent adhesion to most substrates including concrete, plaster, masonry, and metal surfaces.

The membrane formed by application of HYDROCRYL 300 is resistant to ultra violet rays. This allows the product to perform perfectly in direct sun light. Therefore it can be applied to building roofs, hanger roofs, factories, stores and metal sheds.

Uses:

- External water proofing of roofs, hangers, factories on top of concrete or metal or old bituminous water proofing layer.
- Water proofing and reflective layer for metal made sheds and hangers.
- Water proofing and reflective coating to reduce greenhouse effect for farm houses, poultry hangers, and livestock areas.
- Top coat layer in the roofing system comprised of PU foam and water proofing membrane.
- Water proofing and reflective in addition to movement accommodation layer for cold stores, both roof and walls.
- Can be applied as a top coat to EIFS system to ensure proper waterproofing in addition to extra thermal reduction to the system.

Advantages:

- Water based, safe to use, low odor, easy cleaning, environmentally friendly.
- Can be manufactured according to specified colors
- Semi-gloss, has reflective features to reduce heating and reflect direct sunlight.

- Elastomeric – high crack bridging capability
- Excellent adhesion to most common substrates
- Good resistance to chloride and sulphate ions.

Instructions for Use:

Surface Preparation:

All surfaces should be sound, clean, dry and free from loose material, efflorescence, laitance, curing compounds, dirt, oil and grease. Ensure that concrete is cured for at least 28 days.

For application:

- Over bituminous substrates on roofs, ensure the membrane is clean, free from contaminants, with no de-bonding blisters and should be minimum 4-6 months old.
- On top of concrete surface, it is recommended to perform proper cleaning of the substrate to ensure it is free from contaminants and curing compound residue.
- On top of Polyurethane foam, ensure that the surface of the foam is clean, free of dust or contamination. If the PU foam was shaved to slope, ensure the surface is clean without residual before applying HYDROCRYL 300.
- Over steel surfaces, it is recommended to prepare the steel by mechanical means or blasting to ensure proper adhesion.

Application:

HYDROCRYL 300 is a ready to use single component product. To ensure full homogenous mix, shake the pail while closed or mix slowly for 3-5 minutes using a paddle with slow speed drill till a homogenous mix is achieved.

HYDROCRYL 300 can be applied with a roller, trowel, brush or spray machine. It is recommended to apply two coats in case of roller or brush applications. Apply rich coat to the surface in a spread rate of 1.30

HYDROCRYL 300

kg/square meter/coat (500 micron). Subsequent coats to be applied to the first coat with same rate of application preferably at right angles to the first application. Minimum two coats are required, with a thickness of 500 microns per coat to achieve good results. For improved strength and flexibility, embed a 65 g/m² non-woven geotextile membrane, whilst the first coat is still wet and all corner joints, fillets and pipe penetration joints. Allow the coating to fully cure for 7 days to achieve its full properties. Prolonged water stagnation will cause the coating to soften and peel off. Adequate protective measures should be taken when applying in water logging areas.

In applications where movement and foot traffic is expected over the roof, it is recommended to embed a fiber glass mesh in the first coat while fresh. Apply the second coat to cover the mesh fully and ensure proper thickness of material applied.

For porous substrate, or in a very hot climate, it is recommended to apply the first coat of HYDROCRYL 300 diluted with 20% of water.

Standards:

- EN 14891, 1062, 12390
- ASTM D415, C 1305, 4541-02, 2240

TECHNICAL PROPERTIES	
Color	Grey, White
Density	1.30 ± 0.03 kg/lit
Touch Dry	8 hours
Adhesion to Concrete (ASTM D4541-02)	1.0 N/mm ²
Shore A Hardness (ASTM D2240)	45
UV Resistance	No Effect
Tensile Strength (ASTM D412)	1.2 N/mm ²
Elongation (ASTM D412)	>300%
Crack Bridging (BSEN 1062)	>1.5 mm
Water Penetration (BSEN 12390)	NIL
Resistance to Water Pressure (DIN 1048)	>1.5 Bar
Service Temperature	5 to 70°C

Chemical Resistance	Resistant to detergent, oil, general chemicals
---------------------	--

*Values indicated may vary depending on the environment and conditions of the material. Figures given are tested according to standard laboratory conditions.

Coverage:

Minimum two coats are recommended for effective waterproofing membrane. Coverage will vary depending on the porosity of surface and substrate condition. One 20 kg unit will cover approximately 15 square meter (minimum 2 coats) at 1.0 mm thickness

*Coverage rate is an approximate value, and subject to actual site conditions.

Packaging:

Single component: 20 kg in plastic pails

Storage and Shelf life:

Store in original packing in a covered area, in cool, dry place away from direct sunlight and other sources of heat and high humidity condition. The shelf life of the product is up to 12 months if stored as per recommendation. Excessive exposure to sunlight and high humidity may reduce shelf life of the product.

Cleaning:

Clean all tools with water before product hardens. Hardened material can only be removed mechanically.

Notes:

- Do not apply with fog, imminent rain forecast or with weather humidity more than 80%.
- Ponding water is to be avoided for a minimum 72 hours once the membrane is applied.
- HYDROCRYL 300 should not be subjected to permanent water immersion.
- Do not apply on substrates having rising moisture.
- Application to be done preferably during falling ambient and substrate temperatures.

HYDROCRYL 300

Health and Safety:

- Avoid contact with eyes and skin. Wear suitable protective clothing such as coveralls, goggles, dust mask and gloves. Use barrier cream. Ensure that there is adequate ventilation. Do not breathe vapour or spray mist.

FIRST AID:

- Eyes: In the event of accidental splashes, flush with warm water and seek medical advice.
- Skin: Wash skin thoroughly with soap and +
- +water
- Inhalation: Remove to fresh air, keep patient rested
- Ingestion: Do not induce vomiting. Seek immediate medical attention.

For further safety information, please refer to HYDROCRYL 300 Material Safety Data Sheet.

MATEX Rev.04-0223

MATEX warrants that its products are free from material and manufacturing defects. Instructions on how to use the product should be strictly followed to ensure effectivity and safe use. MATEX shall not be liable either directly or indirectly for any damages to personal, equipment or products that may occur as a consequence of the failure of any products application because it has no direct or continuous control over where or how its products are applied. It is the user's responsibility to acquire always the updated version of datasheets.

